

Wood Effect



Remo Porcelain Paving

Designs





Reclaimed Driftwood

Dimensions & Packing Details

300 x 1200 x 20mm

Weight: 44.8kg/m²

Packing Details

	Pieces X Box	Sqm X Box	Boxes X Pallet	Kg X Box	Sqm X Pallet	Kg X Pallet
30x120	2	0.72	32	30.6	23.04	980

Regularity Characteristics

Technical Features	Norms	Required Standard	Performance Value
Straightness of sides	ISO 10545-2	± 0.5% / ± 1.5mm (***)	± 0.08%
Rectangularity (Measurement only on short edges when L/I ≥ 3		± 0.5% / ± 2mm (****)	± 0.1 %
Surface flatness		c.c. ± 0.5% / 2mm e.c. ± 0.5% / 2mm w. ± 0.5% / 2mm	± 0.2% ± 0.2% ± 0.2%

Structural Characteristics

Technical features	Norms	Required Standard	Performance Value
Water absorption level (in% by mass)	ISO 10545-3	E≤ 0,08% Individual Maximum 3%	Average 0.17%

Bulk Mechanical Characteristics

Technical features	Norms	Required Standard	Performance Value
Breaking strength	ISO 10545-4	S ≥ 1300 N	Average 8090.0N
Modulus of rupture		R ≥ 35 N/mm²	Average 39N/mm²

Thermal Characteristics

Technical features	Norms	Required Standard	Performance Value	
Thermal shock resistance	ISO 10545-9	Test passed in accordance with ISO 10545-1	Resistant	



Physical Characteristics

Technical features	Norms	Required Standard	Performance Value
Reaction to fire	-	Class A1 or A1fi	A1 - A1 _{fl}

Chemical Characteristics


Technical features	Norms	Required Standard	Performance Value
Resistance to household chemicals and swimming pool salts		Minimum B class	Conformed to Class AA
Resistance to low concentrations of acids and alkalis	ISO 10545-13	Declared class	Conformed to Class AA
Resistance to high concentrations of acids and alkalis	_	Declared class	Conformed to Class AA
Resistance to staining, for unglazed tiles	ISO 10545-14	Declared class	Conformed to Class AA

Safety Characteristics

Technical features	Norms	Required Standard	Performance Value
Shod Ramp Test	DIN EN 16165 ANNEX B (EX DIN 51130)	Declared value	R11
Barefoot Ramp test	DIN EN 16165 ANNEX A (EX DIN 51097	Declared value	A+B+C
Pendulum friction Test	BS EN 16165 ANNEX C (EX BS 7976)	PTV ≥ 36 classifies the surface as "low slip risk"	≥36Dry ≥36Wet

- (•) Anti-slip performance is guaranteed at the time of delivery of the product.
- (*) The permissible deviation, in % or mm, of the average size for each tile (2 or 4 sides) from work size (W).
- (**) The permissible deviation, in % or mm, of the average thickness for each tile from the work size thickness (W).
- (***) The maximum permissible deviation from straightness, in % or mm, related to the corresponding work sizes (W
- (****) The maximum permissible deviation from rectangularity, in % or mm, related to the corresponding work sizes (W). c.c. The maximum permissible deviation from centre curvature, in % or mm, related to the diagonal calculated from the work sizes (W).
- e.c. The maximum permissible deviation from edge curvature, in % or mm, related to the corresponding work sizes (W).
- w. The maximum permissible deviation from warpage, in % or mm, related to the diagonal calculated from the work sizes (W).

Compatible Systems



Got Questions?

Visit www.rynogroup.co.uk or call us today on +44 (0)203 967 3500 or reach out on sales@rynogroup.co.uk.